



CERTIFIED MATERIAL TEST REPORT

US-ML-CHARLOTTE
6601 LAKEVIEW ROAD
CHARLOTTE, NC 28269
USA

Table with 4 columns: GRADE (GGMULTI), SHAPE / SIZE (Flat Bar / 3/8 X 1), DOCUMENT ID (0000136848), LENGTH (20'00"), WEIGHT (9,180 LB), HEAT / BATCH (54188636/02), SALES ORDER (11580033/000020), CUSTOMER MATERIAL N° (00000000101210020), SPECIFICATION / DATE or REVISION (ASME SA36, ASTM A529-14, etc.), CUSTOMER PURCHASE ORDER NUMBER (4500525404), BILL OF LADING (1321-0000098990), DATE (04/14/2022)

CHEMICAL COMPOSITION table with columns: C (%), Mn (%), P (%), S (%), Si (%), Cu (%), Ni (%), Cr (%), Mo(%), V (%), Nb (%). Values: C 0.14, Mn 0.63, P 0.011, S 0.028, Si 0.19, Cu 0.37, Ni 0.19, Cr 0.21, Mo 0.050, V 0.003, Nb 0.007

MECHANICAL PROPERTIES table with columns: Elong. (%), G/L (Inches), UTS (PSI), UTS (MPa), YS (PSI), YS (MPa). Values: Elong 25.00, 22.50; G/L 8.000, 8.000; UTS 76059, 75926; UTS 524, 524; YS 55114, 54426; YS 380, 375

GEOMETRIC CHARACTERISTICS table with column: R:R. Value: 66.00

COMMENTS / NOTES
This grade meets the requirements for the following grades:
ASTM Grades: A36; A529-50; A572-50; A709-36; A709-50
CSA Grades: 44W; 50W
AASHTO Grades: M270-36; M270-50
ASME Grades: SA36

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdaу possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

Bhaskar Yalamanchili
BHASKAR YALAMANCHILI
QUALITY DIRECTOR

Phone: (409) 267-1071 Email: Bhaskar.Yalamanchili@gerdau.com

Rachel Warren
RACHEL WARREN
QUALITY ASSURANCE MGR.

Phone: (704) 596-0361 EX3039 Email: Rachel.Webster@gerdau.com