

**NUCOR STEEL TUSCALOOSA, INC.**

 Nucor Steel Tuscaloosa, Inc.  
 1700 HOLT RD N.E.  
 Tuscaloosa, AL 35404-1000 USA  
 800 800-8204  
 customerservice@nucortusk.com

Load Number	Tally	Mill Order Number	PO NO   Line NO	Part Number	Certificate Number	Prepared
T311867	0000001090147	N-199858-001	P0236074 1		S09014701-1	10/13/2022 11:49
<b>Grade</b>				<b>Customer:</b>		
<b>Order Description:</b> Hot Roll Plate From Coil A36, 0.1875 IN x 96.000 IN x 240.000 IN				<b>Sold TO:</b> SUPERIOR SUPPLY AND STEEL SULPHUR LA		
<b>Quality Plan Description:</b> A36MODMN-TRIPLE: ASTM A36-19/A709-36/ASME SA36-21/M270-36 MOD MN				<b>Ship TO:</b> SUPERIOR SUPPLY AND STEEL SULPHUR LA		
				<b>Sent TO:</b>		

Shipped Item	Heat/Slab Number	Certified By	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Cb	V	Al	Ti	N2	B	Ca	Sn	CEV	ACI
2G0477DB	22B3772-02 ***	22B3772	0.18	0.87	0.013	0.003	0.04	0.28	0.07	0.07	0.019	0.001	0.004	0.031	0.002	0.008	0.0001	0.0022	0.007	0.37	
2I0961D	22B5099-01 ***	22B5099	0.17	0.84	0.011	0.005	0.06	0.21	0.06	0.07	0.017	0.002	0.004	0.026	0.001	0.006	0.0001	0.0020	0.006	0.35	
2J0612B	22A5403-04 ***	22A5403	0.19	0.87	0.014	0.004	0.05	0.38	0.11	0.08	0.017	0.001	0.003	0.030	0.001	0.010	0.0001	0.0022	0.005	0.39	
2J0612D	22A5403-04 ***	22A5403	0.19	0.87	0.014	0.004	0.05	0.38	0.11	0.08	0.017	0.001	0.003	0.030	0.001	0.010	0.0001	0.0022	0.005	0.39	
2J0613B	22B5404-02 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	
2J0613D	22B5404-02 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	
2J0614B	22B5404-01 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	
2J0614D	22B5404-01 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	
2J0615B	22B5404-04 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	
2J0615D	22B5404-04 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	
2J0616D	22B5404-03 ***	22B5404	0.19	0.86	0.013	0.004	0.04	0.24	0.06	0.07	0.016	0.001	0.003	0.034	0.001	0.009	0.0001	0.0019	0.006	0.37	

Mercury has not come in contact with this product during the manufacturing process nor has any mercury been used by the manufacturing process. Certified in accordance with EN 10204 3.1. No weld repair has been performed on this material. Yield strength is determined by the 0.2% offset method unless otherwise noted. Manufactured to a fully killed fine grain practice. NUTEMPER TEMPER PASSED plate from coil  
 ISO 9001:2015 Registered, PED Certified

We hereby certify that the product described above passed all of the tests required by the specifications.

*Jon Walton*  
 Jon Walton - Metallurgist

\*\*\*\* indicates Heats melted and Manufactured in the U.S.A.

Load Number	Tally	Mill Order Number	PO NO   Line NO	Part Number	Certificate Number	Prepared
T311867	0000001090147	N-199858-001	P0236074 1		S09014701-1	10/13/2022 11:49
<b>Grade</b>				<b>Customer:</b>		
<b>Order Description:</b> Hot Roll Plate From Coil A36, 0.1875 IN x 96.000 IN x 240.000 IN				<b>Sold TO:</b> SUPERIOR SUPPLY AND STEEL SULPHUR LA		
<b>Quality Plan Description:</b> A36MODMN-TRIPLE: ASTM A36-19/A709-36/ASME SA36-21/M270-36 MOD MN				<b>Ship TO:</b> SUPERIOR SUPPLY AND STEEL SULPHUR LA		
				<b>Sent TO:</b>		

Shipped Item	Certified By	Heat/Slab Number	Yield ksi	Tensile ksi	Y/T %	ELONGATION %		Bend OK?	Hard HB	Charpy Impacts (ft-lbs)				Shear %				Test Temp	
						2"	8"			Size mm	1	2	3	Avg	1	2	3		Avg
2G0477DB	S2G0477FTT	22B3772-02 ***	50.4	73.7	68.4	29.4													
2G0477DB	S2G0477MTT	22B3772-02 ***	44.8	66.5	67.4	29.5													
2I0961D	S2I0961FTT	22B5099-01 ***	54.2	75.2	72.1	26.2													
2I0961D	S2I0961MTT	22B5099-01 ***	53.8	73.7	73.0	31.7													
2J0612B	S2J0612FTT	22A5403-04 ***	54.0	75.8	71.2	28.7													
2J0612B	S2J0612MTT	22A5403-04 ***	53.8	71.7	75.0	29.4													
2J0612D	S2J0612FTT	22A5403-04 ***	54.0	75.8	71.2	28.7													
2J0612D	S2J0612MTT	22A5403-04 ***	53.8	71.7	75.0	29.4													
2J0613B	S2J0613FTT	22B5404-02 ***	51.8	74.0	70.0	31.7													
2J0613B	S2J0613MTT	22B5404-02 ***	48.0	66.1	72.6	30.2													
2J0613D	S2J0613FTT	22B5404-02 ***	51.8	74.0	70.0	31.7													
2J0613D	S2J0613MTT	22B5404-02 ***	48.0	66.1	72.6	30.2													
2J0614B	S2J0614FTT	22B5404-01 ***	51.4	72.3	71.1	29.4													
2J0614B	S2J0614MTT	22B5404-01 ***	47.9	66.2	72.4	30.6													
2J0614D	S2J0614FTT	22B5404-01 ***	51.4	72.3	71.1	29.4													
2J0614D	S2J0614MTT	22B5404-01 ***	47.9	66.2	72.4	30.6													
2J0615B	S2J0613FTT	22B5404-04 ***	51.8	74.0	70.0	31.7													
2J0615B	S2J0614FTT	22B5404-04 ***	51.4	72.3	71.1	29.4													

Mercury has not come in contact with this product during the manufacturing process nor has any mercury been used by the manufacturing process. Certified in accordance with EN 10204 3.1. No weld repair has been performed on this material. Yield strength is determined by the 0.2% offset method unless otherwise noted. Manufactured to a fully killed fine grain practice. NUTEMPER TEMPER PASSED plate from coil  
 ISO 9001:2015 Registered, PED Certified

We hereby certify that the product described above passed all of the tests required by the specifications.

*Jon Walton*  
 Jon Walton - Metallurgist

\*\*\*\* indicates Heats melted and Manufactured in the U.S.A.

Nucor Steel Tuscaloosa, Inc.  
 1700 HOLT RD N.E.  
 Tuscaloosa, AL 35404-1000 USA  
 800 800-8204  
 customerservice@nucortusk.com

Load Number	Tally	Mill Order Number	PO NO   Line NO	Part Number	Certificate Number	Prepared
T311867	00000001090147	N-199858-001	P0236074 1		S09014701-1	10/13/2022 11:49
<b>Grade</b>				<b>Customer:</b>		
<b>Order Description:</b> Hot Roll Plate From Coil A36, 0.1875 IN x 96.000 IN x 240.000 IN				<b>Sold TO:</b> SUPERIOR SUPPLY AND STEEL SULPHUR LA		
<b>Quality Plan Description:</b> A36MODMN-TRIPLE: ASTM A36-19/A709-36/ASME SA36-21/M270-36 MOD MN				<b>Ship TO:</b> SUPERIOR SUPPLY AND STEEL SULPHUR LA		
				<b>Sent TO:</b>		

Shipped Item	Certified By	Heat/Slab Number	Yield ksi	Tensile ksi	Y/T %	ELONGATION %		Bend OK?	Hard HB	Charpy Impacts (ft-lbs)				Shear %				Test Temp	
						2"	8"			Size mm	1	2	3	Avg	1	2	3		Avg
2J0615B	S2J0613MTT	22B5404-04 ***	48.0	66.1	72.6	30.2													
2J0615B	S2J0614MTT	22B5404-04 ***	47.9	66.2	72.4	30.6													
2J0615D	S2J0613FTT	22B5404-04 ***	51.8	74.0	70.0	31.7													
2J0615D	S2J0614FTT	22B5404-04 ***	51.4	72.3	71.1	29.4													
2J0615D	S2J0613MTT	22B5404-04 ***	48.0	66.1	72.6	30.2													
2J0615D	S2J0614MTT	22B5404-04 ***	47.9	66.2	72.4	30.6													
2J0616D	S2J0613FTT	22B5404-03 ***	51.8	74.0	70.0	31.7													
2J0616D	S2J0614FTT	22B5404-03 ***	51.4	72.3	71.1	29.4													
2J0616D	S2J0613MTT	22B5404-03 ***	48.0	66.1	72.6	30.2													
2J0616D	S2J0614MTT	22B5404-03 ***	47.9	66.2	72.4	30.6													

Items: 11 PCS: 36 Weight: 44106 LBS

Mercury has not come in contact with this product during the manufacturing process nor has any mercury been used by the manufacturing process. Certified in accordance with EN 10204 3.1. No weld repair has been performed on this material. Yield strength is determined by the 0.2% offset method unless otherwise noted. Manufactured to a fully killed fine grain practice. NUTEMPER TEMPER PASSED plate from coil  
 ISO 9001:2015 Registered, PED Certified

We hereby certify that the product described above passed all of the tests required by the specifications.

*Jon Walton*  
 Jon Walton - Metallurgist

\*\*\*\* indicates Heats melted and Manufactured in the U.S.A.