

Customer PO	4500532892	Sales Order #	11048465 - 9.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	3016780
Grade	Nucor Multigrade	Lot #	110003842560
Size	0.375" x 4"	Heat #	1100038425
BOL #	BOL-1238280	Load #	1143656
Description	Hot Roll - Merchant Bar Quality Flat 3/8" x 4" Nucor Multigrade 20' 0" [240"] 4001-8000 lbs	Customer Part #	101240020
Production Date	08/23/2022	Qty Shipped LBS	14700
Product Country Of Origin	United States	Qty Shipped EA	144
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 08/08/2022

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	Ti (%)	V (%)	Sn (%)
0.12	0.85	0.017	0.015	0.218	0.14	0.25	0.04	0.26	0.001	0.043	0.008

ASTM A529 S78.2 CE (%) : 0.40

**Tensile testing**

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	56900	72500	21.0
(2)	57500	72200	21.0

**Comments:**

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-05(2009) GR50(345); A572/572M-07 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W)& GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
2. Mercury not intentionally added at any point during manufacturing or testing of this material.
3. Welding or weld repair was not performed on this material.
4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

