

REF. B/L: 81158954
 Date: 06/13/2023
 Customer: 1592



Atlas Tube Corp. Kansas City
 Burlington St
 North Kansas City Missouri USA
 64116

Tel:
 Fax:

Sold To

Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

MATERIAL TEST REPORT

Shipped To

Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Material: 3.0x3.0x375x20'0"(6x4)
Material No: 300303752000

Made in: USA
Melted and Poured in: USA

Sales Order: 1920522
Purchase Order: P0242031-01

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
23001291	0.060	0.830	0.011	0.002	0.020	0.026	0.090	0.001	0.015	0.050	0.050	0.004	0.001	0.0002	0.0082	0.0009
Bundle No	PCs	Yield	Tensile	Eln.2in	Certification											
Z200003902	24	068400 Psi	071900 Psi	29.5 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Location	Method	Recycled Content	Post Consumer	Pre-Consumer	% Harvested	Within Miles of Location								
23001291	BIGRIVER	OSCEOLA,AR	EAF	76.00%	95.00%	5.00 %	75%	500								

Material Note:

Sales Or. Note:

Material: 3.0x3.0x375x20'0"(6x4)
Material No: 300303752000

Made in: USA
Melted and Poured in: USA

Sales Order: 1922408
Purchase Order: P0242031-01

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
23001291	0.060	0.830	0.011	0.002	0.020	0.026	0.090	0.001	0.015	0.050	0.050	0.004	0.001	0.0002	0.0082	0.0009
Bundle No	PCs	Yield	Tensile	Eln.2in	Certification											
Z200003899	24	068400 Psi	071900 Psi	29.5 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Location	Method	Recycled Content	Post Consumer	Pre-Consumer	% Harvested	Within Miles of Location								
23001291	BIGRIVER	OSCEOLA,AR	EAF	76.00%	95.00%	5.00 %	75%	500								

Material Note:

Sales Or. Note:

Authorized by Quality Assurance
Jason Richard
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

