

Sold To: SUPERIOR SUPPLY & STEEL
 PO BOX 2388
 SULPHUR, LA 70664 US

Ship To: SUPERIOR SUPPLY
 318 CITIES SERVICE HWY
 HWY-108
 SULPHUR, LA 70663 US

Customer PO	254213-01	Sales Order #	11081514 - 2.1
Product Group	Hot Roll - Merchant Bar Quality	Product #	1047538
Grade	Nucor Multigrade	Lot #	110006151120
Size	0.25" x 3"	Heat #	1100061511
BOL #	BOL-1919598	Load #	1878079
Description	Hot Roll - Merchant Bar Quality Flat 1/4" x 3" Nucor Multigrade 20' 0" [240"] 2001-6000 lbs	Customer Part #	
Production Date	09/05/2024	Qty Shipped LBS	5104
Product Country Of Origin	United States	Qty Shipped EA	100
Original Item Description		Original Item Number	

I hereby certify that the material described herein has been manufactured in accordance with the specifications and standards listed above and that it satisfies those requirements.

Melt Country of Origin : United States

Melting Date: 08/31/2024

Roll Country of Origin : United States

Rolling Date: 09/05/2024

C (%)	Mn (%)	P (%)	S (%)	Si (%)	Ni (%)	Cr (%)	Mo (%)	Cu (%)	Ti (%)	V (%)	Sn (%)
0.13	0.85	0.012	0.020	0.214	0.11	0.15	0.04	0.24	0.000	0.036	0.009

ASTM A529 S78.2 CE (%) : 0.37

Tensile testing

	Yield (PSI)	Tensile (PSI)	Elongation in 8" (%)
(1)	58500	74600	23.0
(2)	59400	75200	21.0

Comments:

NUCOR MULTIGRADE MEETS THE REQUIREMENTS OF: ASTM A36/A36M-14; A529/529M-05(2009) GR50(345); A572/572M-07 GR50(345); A709/709M-10 GR36(250) & GR50(345); CSA G40.21-04 GR44W(300W) & GR50W(350W); AASHTO M270/M270M-10 GR36(270) & GR50(345); ASME SA36/SA36M-07; MEETS REPORTING REQUIREMENTS OF EN10204 SEC 3.1

1. All manufacturing processes of the steel, including melting, casting & hot rolling, have been performed in U.S.A
2. Mercury not intentionally added at any point during manufacturing or testing of this material.
3. Welding or weld repair was not performed on this material.
4. This material conforms to the specifications described on this document and may not be reproduced, except in full, without written approval of Nucor Corporation.
5. Results reported ASTM E45 (Inclusion content) and ASTM E381 (Macro-etch) are provided as interpretation of ASTM procedures.

