

Atlas Tube Alabama  
 171 Cleage Dr  
 Birmingham Alabama USA  
 35217  
 Tel:  
 Fax:



REF.B/L: 81313684  
 Date: 07/31/2025  
 Customer: 1592

**MATERIAL TEST REPORT**

**Sold To**

Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**

Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

<b>Material:</b> 3.0x3.0x250x20'0"0(5x5).	<b>Material No:</b> 0300302502000-B	<b>Made in:</b> USA														
<b>Sales Order:</b> 2222840	<b>Purchase Order:</b> P0258496-01	<b>Melted and Poured in:</b> USA														
		<b>Cust Material#:</b> 982024560														
<b>Heat No</b>	<b>C</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Si</b>	<b>Al</b>	<b>Cu</b>	<b>Cb</b>	<b>Mo</b>	<b>Ni</b>	<b>Cr</b>	<b>V</b>	<b>Ti</b>	<b>B</b>	<b>N</b>	<b>Ca</b>
NQ3944	0.200	0.390	0.012	0.002	0.023	0.027	0.110	0.000	0.020	0.030	0.050	0.004	0.000	0.0000	0.0060	0.0020
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Certification</b>						<b>CE: 0.29</b>					
MA00222557	24	060622 Psi	069376 Psi	28.0 %	ASTM A500-23 GRADE B&C											
<b>Heat</b>	<b>MILL</b>	<b>Mill Location</b>	<b>Method</b>	<b>Recycled_Content</b>	<b>Post_Consumer</b>	<b>Pre-Consumer (Post Industrial)</b>	<b>% Harvested</b>	<b>Within Miles of Location</b>								
NQ3944	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500								

**Material Note:**  
**Sales Or. Note:**

<b>Material:</b> 3.0x3.0x250x20'0"0(5x5).	<b>Material No:</b> 0300302502000-B	<b>Made in:</b> USA														
<b>Sales Order:</b> 2222840	<b>Purchase Order:</b> P0258496-01	<b>Melted and Poured in:</b> USA														
		<b>Cust Material#:</b> 982024560														
<b>Heat No</b>	<b>C</b>	<b>Mn</b>	<b>P</b>	<b>S</b>	<b>Si</b>	<b>Al</b>	<b>Cu</b>	<b>Cb</b>	<b>Mo</b>	<b>Ni</b>	<b>Cr</b>	<b>V</b>	<b>Ti</b>	<b>B</b>	<b>N</b>	<b>Ca</b>
SQ4572	0.190	0.400	0.011	0.004	0.016	0.031	0.110	0.000	0.010	0.030	0.050	0.004	0.000	0.0000	0.0060	0.0020
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Certification</b>						<b>CE: 0.28</b>					
MA00222557	1	054072 Psi	069734 Psi	29.0 %	ASTM A500-23 GRADE B&C											
<b>Heat</b>	<b>MILL</b>	<b>Mill Location</b>	<b>Method</b>	<b>Recycled_Content</b>	<b>Post_Consumer</b>	<b>Pre-Consumer (Post Industrial)</b>	<b>% Harvested</b>	<b>Within Miles of Location</b>								
SQ4572	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500								

**Material Note:**  
**Sales Or. Note:**

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1. Any tubular steel product noted as "Made in USA" and "Melted and Poured in USA" meets the Build America, Buy America Act. Method of manufacture is ERW.

