

Atlas Tube Alabama
 171 Cleage Dr
 Birmingham Alabama USA
 35217
 Tel:
 Fax:



REF.B/L: 81133444
 Date: 01/25/2023
 Customer: 1592

MATERIAL TEST REPORT

Sold To

Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

Shipped To

Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Material: 6.0x4.0x250x20'0"0(3x3). **Material No:** 0600402502000-B **Made in:** USA
Sales Order: 1870566 **Purchase Order:** PO238246-11 **Melted and Poured in:** USA
Cust Material#: 982024945

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
PM7074	0.200	0.400	0.007	0.002	0.020	0.023	0.120	0.000	0.010	0.040	0.050	0.002	0.001	0.0000	0.0080	0.0010

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.29		
MA00150016	9	065313 Psi	070294 Psi	28.7 %	ASTM A500-21 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
PM7074	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500

Material Note:

Sales Or. Note:

Material: 6.0x4.0x250x20'0"0(3x3). **Material No:** 0600402502000-B **Made in:** USA
Sales Order: 1870566 **Purchase Order:** PO238246-11 **Melted and Poured in:** USA
Cust Material#: 982024945

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
PM7074	0.200	0.400	0.007	0.002	0.020	0.023	0.120	0.000	0.010	0.040	0.050	0.002	0.001	0.0000	0.0080	0.0010

Bundle No	PCs	Yield	Tensile	Eln.2in	Certification	CE: 0.29		
MA00150015	9	065313 Psi	070294 Psi	28.7 %	ASTM A500-21 GRADE B&C			
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location
PM7074	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500

Material Note:

Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. This document is in compliance with the requirements of EN 10204 type 3.1

