



CMC STEEL TEXAS
1 STEEL MILL DRIVE
SEGUIN TX 78155-7510

CERTIFIED MILL TEST REPORT
For additional copies call
800-227-6489

We hereby certify that the test results presented here
are accurate and conform to the reported grade specification

Drew M Fischer

Quality Assurance Manager

HEAT NO.:3122090 SECTION: REBAR 16MM (#5) 20'0" 420/60 GRADE: ASTM A615-22 Gr 420/60 ROLL DATE: 04/22/2023 MELT DATE: 04/22/2023 Cert. No.: 85453464 / 122090A371	S O L D T O	Superior Supply & Steel Co 318 N CITIES SERVICE HWY SULPHUR LA US 70663-5424 3376252300 3376258509	S H I P T O	Superior Supply & Steel Co 318 N CITIES SERVICE HWY SULPHUR LA US 70663-5424 3376252300 3376258509	Delivery#: 85453464 BOL#: 75412982 CUST PO#: P0242044-01 CUST P/N: DLVRY LBS / HEAT: 4006.000 LB DLVRY PCS / HEAT: 192 EA
--	----------------------------	---	----------------------------	---	--

Characteristic	Value	Characteristic	Value	Characteristic	Value
C	0.45%	Bend Test Diameter	2.188IN	<p>The Following is true of the material represented by this MTR:</p> <p><i>*Material is fully killed and is Hot Rolled Steel</i></p> <p><i>*100% melted, rolled, and manufactured in the USA</i></p> <p><i>*EN10204:2004 3.1 compliant</i></p> <p><i>*Contains no weld repair</i></p> <p><i>*Contains no Mercury contamination</i></p> <p><i>*Manufactured in accordance with the latest version of the plant quality manual</i></p> <p><i>*Meets the "Buy America" requirements of 23 CFR635.410, 49 CFR 661</i></p> <p><i>*Warning: This product can expose you to chemicals which are known to the State of California to cause cancer, birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov</i></p>	
Mn	0.83%				
P	0.009%				
S	0.051%				
Si	0.18%				
Cu	0.35%				
Cr	0.09%				
Ni	0.22%				
Mo	0.082%				
V	0.000%				
Cb	0.001%				
Sn	0.014%				
Al	0.001%				
Yield Strength test 1	66.7ksi				
Tensile Strength test 1	105.8ksi				
Elongation test 1	12%				
Elongation Gage Lgth test 1	8IN				
Tensile to Yield ratio test1	1.59				
Bend Test 1	Passed				

REMARKS :