

Atlas Tube Alabama  
 171 Cleege Dr  
 Birmingham Alabama USA  
 35217



REF./BL: 81160899  
 Date: 06/23/2023  
 Customer: 1592

Tel:  
 Fax:

**MATERIAL TEST REPORT**

**Sold To**  
 Superior Supply and Steel  
 PO Box 2388  
 SULPHUR LA 70664  
 USA

**Shipped To**  
 Superior Supply and Steel  
 318 North Cities Service Hwy  
 SULPHUR LA 70663  
 USA

Material: 4.0x4.0x120x20"0(4x3). Material No: 0400401202000-B Made in: USA

Sales Order: 1924921 Purchase Order: P0242241-01 Melted and Poured in: USA  
 Cust Material#: 982024435

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	NI	Cr	V	TI	B	N	Ca
A305625	0.210	0.450	0.015	0.003	0.040	0.021	0.090	0.001	0.010	0.030	0.050	0.000	0.001	0.0001	0.0062	0.0017
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Mill Location</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Method</b>	<b>Recycled Content</b>	<b>Post Consumer</b>	<b>Pre-Consumer</b>	<b>Post Industrial</b>	<b>% Harvested</b>	<b>Within Miles of Location</b>				
MA00160127	12	066179 Psi	066179 Psi	069787 Psi	26.5 %	EAF	76.00%	95.00%	5.00 %	75%	500	CE: 0.31				

Heat MILL Columbus,MS Method Recycled Content Post Consumer Pre-Consumer Post Industrial % Harvested Within Miles of Location

Material Note: Material No: 0400402502000-B

Material: 4.0x4.0x250x20"0(4x3). Material No: 0400402502000-B

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	NI	Cr	V	TI	B	N	Ca
TN1987	0.190	0.390	0.006	0.000	0.040	0.030	0.130	0.000	0.010	0.030	0.050	0.003	0.001	0.0000	0.0070	0.0020
<b>Bundle No</b>	<b>PCs</b>	<b>Yield</b>	<b>Mill Location</b>	<b>Tensile</b>	<b>Eln.2in</b>	<b>Method</b>	<b>Recycled Content</b>	<b>Post Consumer</b>	<b>Pre-Consumer</b>	<b>Post Industrial</b>	<b>% Harvested</b>	<b>Within Miles of Location</b>				
MA00158255	12	063483 Psi	063483 Psi	073892 Psi	26.5 %	EAF	53.70%	23.80%	29.90%	86%	500	CE: 0.28				

Heat MILL Decatur,AL Method Recycled Content Post Consumer Pre-Consumer Post Industrial % Harvested Within Miles of Location

Material Note: Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*  
**Jason Richard**

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1

