

 TOSÇELİK Profil ve Sac Adres : Tökrman Bölgesi Bdykdöyöz mah. All libeyli cad.No:18 Toprakale Osmaniyé Türkiye Tel : +90 328 858 20 90 PBX Fax : +90 328 858 22 85 Web : www.toscelik.com.tr E-mail : tosceilik@toscelik.com.tr	TEST SERTİFİKASI MILL TEST CERTIFICATE			Sertifika No/Certificate No : 100034878 Sayfa/Pages : 75/122 Çekim Tarihi/Date of Dispatch : 16.04.2024 Sertifika Tarihi/Certificate Date : 11.05.2024 Sertifika Normu/Certificate Norm : EN 10204-3.1 Satış Belgesi/Order No : 10735088 Sefer No/Order No : 10001006943
	MÜŞTERİ ADI & ADRESİ NAME & ADDRESS OF THE CUSTOMER SUNBELT GROUP L.P. 1980 POST OAK BLVD. SUITE 950 HOUSTON, TX 77058 USA 1 713-840-0550			DESCRIPTION OF GOODS: ERW STEEL PIPES

Sıra No	Tip	Ebatlar	Bar Kodu	Dış Ölçü	MA	Lot No	Üretim Normu	Kalite	YS	TS	E	N, M, S, L	N, Y, B, D	N, Ş, K, R	IE	IE	IE	IE	TT	N, Ş, K, R	N, Ş, K, R	HT	HT	
Revizyon	Type	Size	Barcode	Height	PPS		Product Norm	Steel Grade	psi	psi	%	S, Location	S, Direction	R, Type	J	J	J	J	AV, °C	S, Type	S, Width	psi	Sec.	
445	BPEC	6"X0.280"X21'	P801275659	2402804	7	POW25.896	ASTM A53 / ASME SA53	GRB A53	55985	72809	38.8	BODY	L	F									1780	S
446	BPEC	6"X0.280"X21'	P801275660	2402804	7	POW25.896	ASTM A53 / ASME SA53	GRB A53	55985	72809	38.8	BODY	L	F									1780	S
447	BPEC	6"X0.280"X21'	P801275774	2402804	7	POW25.896	ASTM A53 / ASME SA53	GRB A53	55985	72809	38.8	BODY	L	F									1780	S
448	BPEC	6"X0.280"X21'	P801275775	2402804	7	POW25.896	ASTM A53 / ASME SA53	GRB A53	55985	72809	38.8	BODY	L	F									1780	S
449	BPEC	6"X0.280"X21'	P801275833	2402804	7	POW25.896	ASTM A53 / ASME SA53	GRB A53	55985	72809	38.8	BODY	L	F									1780	S
450	BPEC	6"X0.280"X21'	P801275835	2402804	7	POW25.896	ASTM A53 / ASME SA53	GRB A53	55985	72809	38.8	BODY	L	F									1780	S

Sıra No	Bar Kodu	Tip	C	Si	S	Mn	P	S	Cr	Mo	Ni	Cu	N	Ti	V	Ba	Nb	CEIW	CEPCM	M	Heat Treat	VDC	FT	BD	EX	Non Destruct. Test			B
			%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	%	Type	Temp.				ECT	UT	PA	
445	P801275659	ØP	0.1384	0.1848	0.0108	0.4928	0.0108	0.0289	0.0819	0.0184	0.1052	0.3349	0.0078	0.0018	0.0100	0.0248	0.0029	0.2719	0.1843	OK	WB	550	Q	Q		Q	Q		Q
446	P801275660	ØP	0.1384	0.1848	0.0108	0.4928	0.0108	0.0289	0.0819	0.0184	0.1052	0.3349	0.0078	0.0018	0.0100	0.0248	0.0029	0.2719	0.1843	OK	WB	550	Q	Q		Q	Q		Q
447	P801275774	ØP	0.1384	0.1848	0.0108	0.4928	0.0108	0.0289	0.0819	0.0184	0.1052	0.3349	0.0078	0.0018	0.0100	0.0248	0.0029	0.2719	0.1843	OK	WB	550	Q	Q		Q	Q		Q
448	P801275775	ØP	0.1384	0.1848	0.0108	0.4928	0.0108	0.0289	0.0819	0.0184	0.1052	0.3349	0.0078	0.0018	0.0100	0.0248	0.0029	0.2719	0.1843	OK	WB	550	Q	Q		Q	Q		Q
449	P801275833	ØP	0.1384	0.1848	0.0108	0.4928	0.0108	0.0289	0.0819	0.0184	0.1052	0.3349	0.0078	0.0018	0.0100	0.0248	0.0029	0.2719	0.1843	OK	WB	550	Q	Q		Q	Q		Q
450	P801275835	ØP	0.1384	0.1848	0.0108	0.4928	0.0108	0.0289	0.0819	0.0184	0.1052	0.3349	0.0078	0.0018	0.0100	0.0248	0.0029	0.2719	0.1843	OK	WB	550	Q	Q		Q	Q		Q

G : J/yüklü
 YS : Abma Muk./Yield Strength(N/mm²)
 TS : Çekme Muk./Tensile Strength(N/mm²)
 E : Uzama/Elongation (%)
 B : Havsalı/ Bevelled
 VDC : Görsel Kontrol/ Visual Dimensional Check
 EX : Genişletme/ Expanding
 HT : Hidrostatik Test/ Hydrostatic Test(Bar)
 IE : Darbe Enerjisi/Impact Energy(Joule)
 TT : Test Sıcaklığı/ Test Temp.for Impact Testing(°C)
 FT TIME : Saniye/ Second
 FT : Yassılama/ Flattening
 BD : Bütüne/Bonding

GIP:Ordu/Product WS:Kaynak Dibi/Weld Seam FB:Yön Gövde/Full Body M:Markalama/Marking PIA/PPS/Paket İçi Adet/Pieces per bundle L:Boyuna/Longitudinal T:Enine/Transverse ECT:Eddy Current Test UT:Ultrasonic Test PA:Phased Array F:Doz/Flat P:Bar/Pipe	THE RAW MATERIAL OF THE GOODS ARE NOT RUSSIAN OR BELARUSIAN ORIGIN AS ACCORDING TO EU REGULATION 833/2014 THE MATERIAL TO WHICH THIS NTR REFERS WAS MANUFACTURED IN TURKEY. BPEC:COATED BLACK PLAIN END	ONAY / APPROVED BY ERW Fabrikaları Kalite Müdürü / ERW Plants Quality Manager Bülent DÖNMEZ  TOSÇELİK Profil ve Sac Organize Sanayi Bölgesi 80950 TOPRAKALEJOSMANIYE TÜRKİYE T + (328) 826 80 80 Fax : (0328) 828 80 09 Asım Gündüz V.D: 086 001 3021
--	---	---

Bu Sertifika TOSÇELİK PROFİL, SAC VE END, A.B. tarafından yapılan standartlara ve ilgili kurumlara uygun olduğuna teyit edilmiştir.
 These results are certified by TOSÇELİK PROFİL, SAC VE END, A.B. and comply with the requirements of the product description