



CERTIFIED MATERIAL TEST REPORT

US-ML-CARTERSVILLE
 384 OLD GRASSDALE ROAD NE
 CARTERSVILLE, GA 30121
 USA

		GRADE GGMULTI	SHAPE / SIZE Misc Channel / 7 X 19.1#	DOCUMENT ID: 0000560414
		LENGTH 40'00"	WEIGHT 9,168 LB	HEAT / BATCH 55072377/05
SALES ORDER 12459878/000190		CUSTOMER MATERIAL N°		SPECIFICATION / DATE or REVISION ASTM A529-14, A572-15 ASTM A6-17, A36-14, ASME SA-36 ASTM A709-17, AASHTO M270-15 CSA G40.20-13/G40.21-13
CUSTOMER PURCHASE ORDER NUMBER SSW132136	BILL OF LADING 1323-0000223843	DATE 12/01/2022		

CHEMICAL COMPOSITION													
C (%)	Mn (%)	P (%)	S (%)	Si (%)	Cu (%)	Ni (%)	Cr (%)	Mo(%)	V (%)	Nb (%)	N (%)	CEqvA6 (%)	Sn (%)
0.08	0.97	0.016	0.026	0.21	0.30	0.11	0.14	0.032	0.002	0.021	0.0090	0.30	0.009

MECHANICAL PROPERTIES						
Elong. (%)	G/L (Inches)	UTS (PSI)	UTS (MPa)	YS 0.2% (PSI)	YS (MPa)	
26.30	8.000	74500	514	58000	400	
26.60	8.000	74700	515	57700	398	

COMMENTS / NOTES

This grade meets the requirements for the following grades:
 ASTM Grades: A36; A529-50; A572-50; A709-36; A709-50
 CSA Grades: 44W; 50W
 AASHTO Grades: M270-36; M270-50
 ASME Grades: SA36

The above figures are certified chemical and physical test records as contained in the permanent records of the company. We certify that these data are correct and in compliance with specified requirements. No weld repair was performed on this material. The material has not been in contact with mercury while in Gerdau possession. For all products other than billets or beam blanks, this material was produced (Electric Arc Furnace, Melted, Continuously Cast, Hot Rolled and, if applicable, Cold-Drawn) in the USA. For billets or beam blanks, this material was produced (Electric Arc Furnace, Melted and Continuously Cast) in the USA. CMTR complies with EN 10204 3.1.

BHASKAR YALAMANCHILI
 QUALITY DIRECTOR

Phone: (409) 267-1071 Email: Bhaskar.Yalamanchili@gerdau.com

YAN WANG
 QUALITY ASSURANCE MGR.

Phone: (770) 387 5718 Email: yan.wang@gerdau.com