





Manufacturer / Fabricante 		Type of document / Tipo de documento <b>INSPECTION CERTIFICATE</b> CERTIFICADO DE INSPECCION according to / de acuerdo con <b>EN 10204-3.1</b>		Document number / N° de certificado: 09/12/2022 <b>0000589079 /</b> Page / Pagina: <b>1 / 2</b>																																	
1 Steel Drive; P.O. Box 13000; Calvert, AL 36513-1300 P1		Customer's order number / N° de Pedido Cliente: 108151		Manufacturer's works order no. / N° de Pedido Manufactura: 901314043 / 001																																	
		Delivery note no. / N° de Entrega: 85794988 / 010		Product / Producto: Stainless Steel Cold Rolled Coil/Bobina																																	
Terms of delivery / Condiciones de entrega ASTM A240/A240M-22, ASME SA-240 Sec. II part A Ed.2021 ASTM A480/A480M-22, ASME SA-480 Sec. II part A Ed.2019 ASTM A276-17, A312-21, A479-22, A484-21b Chemical only ASTM A666-15 ASTM F899-20 for Chemical composition ASME SA312-19, SA479-21 for Chemical Composition ASME SA-276 Sec. II Part A Ed. 2021 for Chemical Composition SAE AMS 5507 H SAE AMS 5524 M SAE AMS QQ-S-763D for Chemical composition. NACE MR0103 / ISO 17945: 2015 NACE MR0175 / ISO 15156-3: 2015 EN 10028-7: 2016		Steel Grade and Quality / Acero UNS S31603 UNS S31600 TYPE 316L/316 1.4404 1.4401																																			
Customer's material no. / N° de material del cliente 9849		Product dimensions (Thickness / Width / Length) / Dimensiones (Espesor / Ancho / Largo) 1.22 mm x 1,219.20 mm 0.0480 inch x 48.0000 inch		Steelmaking procedure / Proceso de manufact. AOD																																	
				Finish / Acabado IIIc / 2B																																	
<table border="1"> <thead> <tr> <th>Packing-No. / N° de Empaque</th> <th>No. of pieces / Piezas</th> <th>Actual weight / Peso actual</th> <th>Actual length / Longitud actual</th> <th>Coil-No. / Bobina No.</th> <th>Heat No. / Colada</th> <th>Inspection lot / Lote de inspeccion</th> <th>Inspection lot / Lote de inspeccion</th> </tr> </thead> <tbody> <tr> <td>3476892</td> <td>1</td> <td>16,579 lb / 7,520 kg</td> <td>2,087 ft / 636 m</td> <td>949626</td> <td>539630</td> <td>1000826024</td> <td>1000826025</td> </tr> <tr> <td>3476899</td> <td>1</td> <td>16,535 lb / 7,500 kg</td> <td>2,087 ft / 636 m</td> <td>949626</td> <td>539630</td> <td>1000826024</td> <td>1000826025</td> </tr> <tr> <td>Sum / Suma</td> <td>2</td> <td>33,114 lb / 15,020 kg</td> <td></td> <td></td> <td></td> <td></td> <td></td> </tr> </tbody> </table>		Packing-No. / N° de Empaque	No. of pieces / Piezas	Actual weight / Peso actual	Actual length / Longitud actual	Coil-No. / Bobina No.	Heat No. / Colada	Inspection lot / Lote de inspeccion	Inspection lot / Lote de inspeccion	3476892	1	16,579 lb / 7,520 kg	2,087 ft / 636 m	949626	539630	1000826024	1000826025	3476899	1	16,535 lb / 7,500 kg	2,087 ft / 636 m	949626	539630	1000826024	1000826025	Sum / Suma	2	33,114 lb / 15,020 kg									
Packing-No. / N° de Empaque	No. of pieces / Piezas	Actual weight / Peso actual	Actual length / Longitud actual	Coil-No. / Bobina No.	Heat No. / Colada	Inspection lot / Lote de inspeccion	Inspection lot / Lote de inspeccion																														
3476892	1	16,579 lb / 7,520 kg	2,087 ft / 636 m	949626	539630	1000826024	1000826025																														
3476899	1	16,535 lb / 7,500 kg	2,087 ft / 636 m	949626	539630	1000826024	1000826025																														
Sum / Suma	2	33,114 lb / 15,020 kg																																			
Heat / Colada 539630		Country of Melt / Pais de colada USA		Chemical composition / Composicion Quimica Chemical analysis per ASTM A751-14a																																	
				<table border="1"> <thead> <tr> <th>% C</th> <th>% Si</th> <th>% Mn</th> <th>% P</th> <th>% S</th> <th>% Cr</th> <th>% Mo</th> <th>% Ni</th> <th>% N</th> <th>% Cu</th> <th>% Co</th> </tr> </thead> <tbody> <tr> <td>0.022</td> <td>0.42</td> <td>1.44</td> <td>0.028</td> <td>0.0013</td> <td>16.54</td> <td>2.01</td> <td>10.05</td> <td>0.037</td> <td>0.43</td> <td>0.22</td> </tr> </tbody> </table>		% C	% Si	% Mn	% P	% S	% Cr	% Mo	% Ni	% N	% Cu	% Co	0.022	0.42	1.44	0.028	0.0013	16.54	2.01	10.05	0.037	0.43	0.22										
% C	% Si	% Mn	% P	% S	% Cr	% Mo	% Ni	% N	% Cu	% Co																											
0.022	0.42	1.44	0.028	0.0013	16.54	2.01	10.05	0.037	0.43	0.22																											
Sample Position / Localiz. de la muestra TRANSVERSE		Mechanical testing per ASTM A370-18																																			
<table border="1"> <thead> <tr> <th>Inspection lot / Lote de inspeccion</th> <th>YS0.2% PSI / MPa</th> <th>YS1,0 PSI / MPa</th> <th>TS PSI / MPa</th> <th>El. A80 %</th> <th>El. 2" %</th> <th>HRB</th> </tr> </thead> <tbody> <tr> <td>1000826024</td> <td>43,945 / 303</td> <td>50,761 / 350</td> <td>92,095 / 635</td> <td>46</td> <td>49</td> <td>81</td> </tr> <tr> <td>1000826025</td> <td>42,059 / 290</td> <td>49,166 / 339</td> <td>91,080 / 628</td> <td>48</td> <td>51</td> <td>80</td> </tr> </tbody> </table>		Inspection lot / Lote de inspeccion	YS0.2% PSI / MPa	YS1,0 PSI / MPa	TS PSI / MPa	El. A80 %	El. 2" %	HRB	1000826024	43,945 / 303	50,761 / 350	92,095 / 635	46	49	81	1000826025	42,059 / 290	49,166 / 339	91,080 / 628	48	51	80															
Inspection lot / Lote de inspeccion	YS0.2% PSI / MPa	YS1,0 PSI / MPa	TS PSI / MPa	El. A80 %	El. 2" %	HRB																															
1000826024	43,945 / 303	50,761 / 350	92,095 / 635	46	49	81																															
1000826025	42,059 / 290	49,166 / 339	91,080 / 628	48	51	80																															
Resistant to intergranular corrosion / Resistente contra corrosión inter-granular: Dimensions-surface / Dimensiones-Superficie: Positive Material Identification (PMI) / Control de identidad (análisis espectrográfico):		ASTM A 262-15, PRACTICE E - Sample Acceptable OK OK																																			
Heat Treat: Solution anneal 1900°F/1040°C Min, Air and water quench																																					
Originator of the document / Originador del documento / <b>Outokumpu Stainless USA, LLC</b> An ISO 9001:2015 certified company ISO 17025:2017 accredited testing lab by ANAB EU PED 2014/68/EU, Annex I, 4.3 certified Certificate is generated automatically / Certificado es generado automáticamente		The information provided is a true copy of data on file / Los valores mostrados corresponden a los datos archivados  Arturo Hernandez Rubio Name of expert / Nombre del experto		Date of issue and validation / Fecha de emisión y validación 09/12/2022 This document shall not be altered or reproduced, except in full. Fraudulent, fictitious, or false statements or entries may be prosecuted by law.																																	

<p>Manufacturer / Fabricante</p> 	<p>Type of document / Tipo de documento</p> <p align="center"><b>INSPECTION CERTIFICATE</b>          CERTIFICADO DE INSPECCION          according to / de acuerdo con  <b>EN 10204-3.1</b></p>	<p>Document number / 09/12/2022          N° de certificado.</p> <p align="center"><b>0000589079 /</b></p> <p>Page / Pagina:  <b>2 / 2</b></p>
<p>DFARS 225.872-1 Compliant          Bending test per ASTM E290-14 OK          No welding or weld repairs were performed on this material          No intentional additions of Mercury compounds were made or used          Free of radioactive contamination          EU RoHS Directive 2011/65/EU Compliant          Country of Melt as per ISO 3166-1</p>		
<p>Originator of the document / Originador del documento /</p> <p><b>Outokumpu Stainless USA, LLC</b>          An ISO 9001:2015 certified company          ISO 17025:2017 accredited testing lab by ANAB          EU PED 2014/68/EU, Anex I, 4.3 certified</p> <p>Certificate is generated automatically /          Certificado es generado automaticamente</p>	<p>The information provided is a true copy of data on file /          Los valores mostrados corresponden a los datos archivados</p>  <p align="center">Arturo Hernandez Rubio          Name of expert / Nombre del experto</p>	<p>Date of issue and validation          Fecha de emisión y validación</p> <p align="center">09/12/2022</p> <p>This document shall not be altered          or reproduced, except in full.          Fraudulent, fictitious, or          false statements or entries          may be prosecuted by law.</p>