

Atlas Tube Alabama
 171 Cleage Dr
 Birmingham Alabama USA
 35217
 Tel:
 Fax:



REF B/L: 81172824
 Date: 09/11/2023
 Customer: 1592

MATERIAL TEST REPORT

Sold To
 Superior Supply and Steel
 PO Box 2388
 SULPHUR LA 70664
 USA

Shipped To
 Superior Supply and Steel
 318 North Cities Service Hwy
 SULPHUR LA 70663
 USA

Material: 3.0X3.0X120X24.0(5x5)

Material No: 0300301202400-B

Made in: USA
 Melted and Poured in: USA
 Cust Material#: 982024433

Sales Order: 1948436

Purchase Order: P0243801-01

CE: 0.28

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
SN5495	0.200	0.370	0.006	0.003	0.019	0.032	0.120	0.000	0.010	0.030	0.030	0.002	0.000	0.0000	0.0050	0.0020
Bundle No	PCs	Yield	Tensile	Eln.2in	Certification											
MA00166203	5	069727 Psi	076410 Psi	26.4 %	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location								
SN5495	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500								

Material Note:

Material: 4.0X3.0X250X20"0(4x4)

Material No: 0400302502000-B

Made in: USA
 Melted and Poured in: USA
 Cust Material#: 982024755

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
SN5521	0.200	0.410	0.005	0.002	0.027	0.030	0.130	0.000	0.010	0.040	0.040	0.002	0.001	0.0000	0.0060	0.0020
Bundle No	PCs	Yield	Tensile	Eln.2in	Certification											
MA00167034	16	000000 Psi	000000 Psi	%	ASTM A500-21 GRADE B&C											
Heat	MILL	Mill Location	Method	Recycled Content	Post Consumer	Pre-Consumer (Post Industrial)	% Harvested	Within Miles of Location								
SN5521	NUCOR	Decatur,AL	EAF	53.70%	23.80%	29.90%	86%	500								

Material Note:

Sales Or. Note:

Authorized by Quality Assurance *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type 3.1

