



American Metal Group
290 Lower Bon Air Road
Sylacauga, AL 35150
Tel 205.433.6680

**234408 LOT 1.032 234408 LOT 1.032 (HEAT
ACTUALS MASS EDIT)**

Heat: **234408 LOT 1.032**

Grade: **1018**

Rolled Mill: **Alton Steel, Inc**

Melted Mill: **Alton Steel, Inc**

Note: **CDR 1018 1.00 x 240 Meets ASTM A108-18
specification Meets ASTM A29 specification**

Material Specification Type	Material Specification	Actual
Chemistry	Carbon	0.16 %
	Manganese	0.88 %
	Phosphorus (max)	0.013 %
	Sulfur (max)	0.027 %
	Silicon	0.19 %
	Copper	0.2 %
	Nickel	0.08 %
	Chromium	0.144 %
	Molybdenum	0.021 %
	Vanadium	0.038 %
	Columbium	0.004 %
	Aluminum	0.003 %

No weld repair performed on the material.
No Mercury used in the production of this material.
Meets EN10204 3.1