



SPS Coil Processing Tulsa  
 5275 Bird Creek Ave.  
 Port of Catoosa, OK 74015

# METALLURGICAL TEST REPORT

PAGE 1 of 1  
 DATE 09/17/2024  
 TIME 13:23:37

S  
O  
L  
D  
  
T  
O

H  
I  
P  
  
T  
O

Order	Material No.	Description	Quantity	Weight	Customer Part	Customer PO	Ship Date
40429183-0010	753754896	3/8 48 X 96 A786 FLOOR PLATE	14	7,333.760			09/17/2024

### Chemical Analysis

Heat No.	Vendor	DOMESTIC		Mill	Melted and Manufactured in the USA										
					Country of Origin: USA										
Carbon	Manganese	Phosphorus	Sulphur	Silicon	Nickel	Chromium	Molybdenum	Boron	Copper	Aluminum	Titanium	Vanadium	Columbium	Nitrogen	Tin
A401401															
0.0600	0.3200	0.0090	0.0020	0.0200	0.0500	0.0500	0.0100	0.0001	0.1200	0.0320	0.0010	0.0000	0.0000	0.0073	0.0070

### Mechanical / Physical Properties

Mill Coil No.	Tensile (PSI)	Yield (PSI)	% Elong (2 in)	Rckwl	Grain	Charpy	Charpy Dr	Charpy Sz	Temperature	Olsen
24B827456										
Batch 1001954254	14 EA	7,333.760 LB			Batch 1001954271	4 EA	2,095.360 LB	Batch 1001954243	15 EA	7,857.600 LB