

Atlas Tube Canada
 200 Clark St.
 Harrow Ontario Canada
 NOR 1G0
 Tel: 519-738-3541
 Fax: 519-738-3537



REF./L: 81231449
 Date: 07/11/2024
 Customer: 1746

Sold To

MATERIAL TEST REPORT

Shipped To

Material: 10.0x5.0x313x40'0"0(1x1).CTMIL Material No: 100050313 Made in: Canada
 Sales Order: 2032288 Purchase Order: SSW142215 Melted and Poured in: Canada
 Heat No C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca
 716520 0.190 0.840 0.011 0.008 0.017 0.046 0.044 0.006 0.006 0.025 0.040 0.002 0.002 0.0002 0.0040 0.0002
 Bundle No PCs Yield Tensile Eln.2in Certification CE: 0.35
 0003710028 1 061696 Psi 073970 Psi 30.0 % ASTM A500-23 GRADE B&C
 Heat MILL Mill Location Method Recycled Content Post Consumer Pre-Consumer (Post Industrial) % Harvested Within Miles of Location
 716520 STELCO Nanticoke,ON BOF 36.90% 19.80% 14.40% 100% 1000
 Material Note:
 Sales Or. Note:

Material: 10.0x5.0x313x40'0"0(1x1).CTMIL Material No: 100050313 Made in: Canada
 Sales Order: 2032288 Purchase Order: SSW142215 Melted and Poured in: Canada
 Heat No C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca
 716520 0.190 0.840 0.011 0.008 0.017 0.046 0.044 0.006 0.006 0.025 0.040 0.002 0.002 0.0002 0.0040 0.0002
 Bundle No PCs Yield Tensile Eln.2in Certification CE: 0.35
 0003710030 1 061696 Psi 073970 Psi 30.0 % ASTM A500-23 GRADE B&C
 Heat MILL Mill Location Method Recycled Content Post Consumer Pre-Consumer (Post Industrial) % Harvested Within Miles of Location
 716520 STELCO Nanticoke,ON BOF 36.90% 19.80% 14.40% 100% 1000
 Material Note:
 Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



Atlas Tube Canada
 200 Clark St.
 Harrow Ontario Canada
 NOR 160
 Tel: 519-738-3541
 Fax: 519-738-3537



REF. B/L: 81231449
 Date: 07/11/2024
 Customer: 1746

Date: 11/1/2024 To: SENTRY SUPPLY dba SO#: A847405 Lm#: 1 PO#: P0252763-08 Part: T0500252548* Qty: 2
 Head#: 306713* Tag: B12103124 Page: 2 of 6

MATERIAL TEST REPORT

Sold To

Shipped To

Material: 5.0x2.5x250x40'0"0(4x4). Material No: 500252504000 Made in: USA
 Sales Order: 2055776 Purchase Order: SSW143618 Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
302750	0.210	0.560	0.009	0.002	0.020	0.020	0.080	0.001	0.020	0.030	0.080	0.002	0.001	0.0000	0.0080	0.0020
<u>Bundle No</u>	<u>PCs</u>	<u>Yield</u>	<u>Tensile</u>	<u>Eln.2in</u>	<u>Certification</u>											
M301443884	2	056371 Psi	074320 Psi	29.9 %	ASTM A500-23 GRADE B&C											
<u>Heat</u>	<u>MILL</u>	<u>Mill Location</u>	<u>Method</u>	<u>Recycled Content</u>	<u>Post Consumer</u>	<u>Pre-Consumer (Post Industrial)</u>	<u>% Harvested</u>	<u>Within Miles of Location</u>								
302750	NORTHSTAR	Delta,OH	EAF	75.00%	30.00%	30.00%	95%	500								

Material Note:
 Sales Or. Note:

Material: 5.0x2.5x250x40'0"0(4x4). Material No: 500252504000 Made in: USA
 Sales Order: 2055776 Purchase Order: SSW143618 Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
306713	0.190	0.520	0.011	0.002	0.020	0.020	0.100	0.001	0.010	0.040	0.090	0.002	0.001	0.0000	0.0060	0.0020
<u>Bundle No</u>	<u>PCs</u>	<u>Yield</u>	<u>Tensile</u>	<u>Eln.2in</u>	<u>Certification</u>											
M301443884	14	060192 Psi	072102 Psi	30.0 %	ASTM A500-23 GRADE B&C											
<u>Heat</u>	<u>MILL</u>	<u>Mill Location</u>	<u>Method</u>	<u>Recycled Content</u>	<u>Post Consumer</u>	<u>Pre-Consumer (Post Industrial)</u>	<u>% Harvested</u>	<u>Within Miles of Location</u>								
306713	NORTHSTAR	Delta,OH	EAF	75.00%	30.00%	30.00%	95%	500								

Material Note:
 Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



Atlas Tube Canada
 200 Clark St.
 Harrow Ontario Canada
 NOR 1G0
 Tel: 519-738-3541
 Fax: 519-738-3537



REF.B/L: 81231449
 Date: 07/11/2024
 Customer: 1746

Date: 11/1/2024 To: SENTRY SUPPLY dba SO#: A847405 Ln#: 1 PO#: P0252763-08 Part: T0500252548* Qty: 2
 Head#: 306713* Tag: B12103124 Page: 3 of 6

Sold To

MATERIAL TEST REPORT

Shipped To

Material: 5.0x2.5x250x40'0"0(4x4). Material No: 500252504000 Made in: USA
 Sales Order: 2055820 Purchase Order: SSW143618 Melted and Poured in: USA

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
302750	0.210	0.560	0.009	0.002	0.020	0.020	0.080	0.001	0.020	0.030	0.080	0.002	0.001	0.0000	0.0080	0.0020
<u>Bundle No</u>	<u>PCs</u>	<u>Yield</u>	<u>Tensile</u>	<u>Eln.2in</u>	<u>Certification</u>											
M301443888	2	056371 Psi	074320 Psi	29.9 %	ASTM A500-23 GRADE B&C											
<u>Heat</u>	<u>MILL</u>	<u>Mill Location</u>	<u>Method</u>	<u>Recycled Content</u>	<u>Post Consumer</u>	<u>Pre-Consumer (Post Industrial)</u>	<u>% Harvested</u>	<u>Within Miles of Location</u>								
302750	NORTHSTAR	Delta,OH	EAF	75.00%	30.00%	30.00%	95%	500								

Material Note:
 Sales Or. Note:

Material: 5.0x2.5x250x40'0"0(4x4). Material No: 500252504000 Made in: USA
 Sales Order: 2055820 Purchase Order: SSW143618 Melted and Poured in: Canada

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
861882	0.180	0.770	0.012	0.010	0.018	0.036	0.066	0.002	0.004	0.027	0.047	0.003	0.002	0.0002	0.0030	0.0002
<u>Bundle No</u>	<u>PCs</u>	<u>Yield</u>	<u>Tensile</u>	<u>Eln.2in</u>	<u>Certification</u>											
M301443888	14	061519 Psi	070321 Psi	32.7 %	ASTM A500-23 GRADE B&C											
<u>Heat</u>	<u>MILL</u>	<u>Mill Location</u>	<u>Method</u>	<u>Recycled Content</u>	<u>Post Consumer</u>	<u>Pre-Consumer (Post Industrial)</u>	<u>% Harvested</u>	<u>Within Miles of Location</u>								
861882	STELCO	Naticoke,ON	BDF	36.90%	19.80%	14.40%	100%	1000								

Material Note:
 Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



Atlas Tube Canada
 200 Clark St.
 Harrow Ontario Canada
 NOR 1G0
 Tel: 519-738-3541
 Fax: 519-738-3537



REF.B/L: 81231449
 Date: 07/11/2024
 Customer: 1746

Date: 11/1/2024 To: SENTRY SUPPLY dba SO#: A847405 Ln#: 1 PO#: P0252763-08 Part: T0500252548* Qty: 2
 Heat#: 306713* Tag: B12103124 Page: 4 of 6

MATERIAL TEST REPORT

Sold To

Shipped To

Material: 5.0x2.5x250x48'0"0(4x3). Material No: 500252504800 Made in: USA
 Sales Order: 2055776 Purchase Order: SSW143618 Melted and Poured in: USA
 Heat No C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca
 306713 0.190 0.520 0.011 0.002 0.020 0.020 0.100 0.001 0.010 0.040 0.090 0.002 0.001 0.0000 0.0060 0.0020
Bundle No PCs Yield Tensile Eln.2in Certification CE: 0.31
 M301443881 12 060192 Psi 072102 Psi 30.0 % ASTM A500-23 GRADE B&C
Heat MILL Mill Location Method Recycled Content Post Consumer Pre-Consumer (Post Industrial) % Harvested Within Miles of Location
 306713 NORTHSTAR Delta,OH EAF 75.00% 30.00% 30.00% 95% 500
 Material Note:
 Sales Or. Note:

Material: 5.0x2.5x250x48'0"0(4x3). Material No: 500252504800 Made in: USA
 Sales Order: 2055776 Purchase Order: SSW143618 Melted and Poured in: USA
 Heat No C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca
 306713 0.190 0.520 0.011 0.002 0.020 0.020 0.100 0.001 0.010 0.040 0.090 0.002 0.001 0.0000 0.0060 0.0020
Bundle No PCs Yield Tensile Eln.2in Certification CE: 0.31
 M301443880 12 060192 Psi 072102 Psi 30.0 % ASTM A500-23 GRADE B&C
Heat MILL Mill Location Method Recycled Content Post Consumer Pre-Consumer (Post Industrial) % Harvested Within Miles of Location
 306713 NORTHSTAR Delta,OH EAF 75.00% 30.00% 30.00% 95% 500
 Material Note:
 Sales Or. Note:

Authorized by Quality Assurance:

Jason Richard
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



Atlas Tube Canada
 200 Clark St.
 Harrow Ontario Canada
 NOR 1G0
 Tel: 519-738-3541
 Fax: 519-738-3537



REF./L: 81231449
 Date: 07/11/2024
 Customer: 1746

MATERIAL TEST REPORT

Sold To

Shipped To

Material: 14.0x6.0x188x40'0"0(1x3). Material No: 1400601884000 Made in: Canada
 Sales Order: 2060753 Purchase Order: SSW143618 Melted and Poured in: Canada

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
717336	0.160	0.740	0.010	0.010	0.015	0.040	0.045	0.002	0.007	0.021	0.053	0.002	0.002	0.0002	0.0040	0.0002
<u>Bundle No</u>	<u>PCs</u>	<u>Yield</u>	<u>Tensile</u>	<u>ELn.2in</u>	<u>Certification</u>											
M201782050	3	058796 Psi	069984 Psi	35.8 %	ASTM A500-23 GRADE B&C											
<u>Heat</u>	<u>MILL</u>	<u>Mill Location</u>	<u>Method</u>	<u>Recycled Content</u>	<u>Post Consumer</u>	<u>Pre-Consumer (Post Industrial)</u>	<u>% Harvested</u>	<u>Within Miles of Location</u>								
717336	STELCO	Nanticoke,ON	BOF	36.90%	19.80%	14.40%	100%	1000								

Material Note:
 Sales Or. Note:

Material: 14.0x6.0x188x40'0"0(1x3). Material No: 1400601884000 Made in: Canada
 Sales Order: 2060753 Purchase Order: SSW143618 Melted and Poured in: Canada

Heat No	C	Mn	P	S	Si	Al	Cu	Cb	Mo	Ni	Cr	V	Ti	B	N	Ca
717336	0.160	0.740	0.010	0.010	0.015	0.040	0.045	0.002	0.007	0.021	0.053	0.002	0.002	0.0002	0.0040	0.0002
<u>Bundle No</u>	<u>PCs</u>	<u>Yield</u>	<u>Tensile</u>	<u>ELn.2in</u>	<u>Certification</u>											
M201782049	3	058796 Psi	069984 Psi	35.8 %	ASTM A500-23 GRADE B&C											
<u>Heat</u>	<u>MILL</u>	<u>Mill Location</u>	<u>Method</u>	<u>Recycled Content</u>	<u>Post Consumer</u>	<u>Pre-Consumer (Post Industrial)</u>	<u>% Harvested</u>	<u>Within Miles of Location</u>								
717336	STELCO	Nanticoke,ON	BOF	36.90%	19.80%	14.40%	100%	1000								

Material Note:
 Sales Or. Note:

Authorized by Quality Assurance:

Jason Richard
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



Date: 11/1/2024 To: SENTRY SUPPLY dba SO#: A817405 Ln#: 1 PO#: P0252763-08 Part: T0500252548* Qty: 2
 Heat#: 306713* Tag: B12103124 Page: 5 of 6

Atlas Tube Canada
 200 Clark St.
 Harrow Ontario Canada
 NOR 160
 Tel: 519-738-3541
 Fax: 519-738-3537



REF.B/L: 81231449
 Date: 07/11/2024
 Customer: 1746

Sold To

MATERIAL TEST REPORT

Shipped To

Material: 14.0x6.0x188x48'0"0(1x3). Material No: 1400601884800 Made in: Canada
 Sales Order: 2060753 Purchase Order: SSW143618 Melted and Poured in: Canada
 Heat No C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca
 717336 0.160 0.740 0.010 0.010 0.015 0.040 0.045 0.002 0.007 0.021 0.053 0.002 0.002 0.0002 0.0040 0.0002
 Bundle No M201782054 PCs 3 Yield 058796 Psi Tensile 069984 Psi Eln.2in 35.8 % Certification ASTM A500-23 GRADE B&C CE: 0.30
 Heat 717336 MILL STELCO Mill Location Naticoke,ON Method BOF Recycled Content 36.90% Post Consumer 19.80% Pre-Consumer (Post Industrial) 14.40% % Harvested 100% Within Miles of Location 1000
 Material Note:
 Sales Or. Note:

Material: 14.0x6.0x188x48'0"0(1x3). Material No: 1400601884800 Made in: Canada
 Sales Order: 2060753 Purchase Order: SSW143618 Melted and Poured in: Canada
 Heat No C Mn P S Si Al Cu Cb Mo Ni Cr V Ti B N Ca
 717336 0.160 0.740 0.010 0.010 0.015 0.040 0.045 0.002 0.007 0.021 0.053 0.002 0.002 0.0002 0.0040 0.0002
 Bundle No M201782053 PCs 3 Yield 058796 Psi Tensile 069984 Psi Eln.2in 35.8 % Certification ASTM A500-23 GRADE B&C CE: 0.30
 Heat 717336 MILL STELCO Mill Location Naticoke,ON Method BOF Recycled Content 36.90% Post Consumer 19.80% Pre-Consumer (Post Industrial) 14.40% % Harvested 100% Within Miles of Location 1000
 Material Note:
 Sales Or. Note:

Authorized by Quality Assurance: *Jason Richard*
Jason Richard

The results reported on this report represent the actual attributes of the material furnished and indicate full compliance with all applicable specification and contract requirements. CE calculated using the AWS D1.1 method. Steel is purchased fully killed with a fine grain practice. This document is in compliance with the requirements of EN10204 type3.1



Date: 11/11/2024 To: SENTRY SUPPLY dba SO#: A847405 Ln#: 1 PO#: P0252763-08 Part: T0500252548* Qty: 2
 Heat#: 306713* Tag: B12103124 Page: 6 of 6